

UXL65-12



Physical Specification





Part Number:	UXL65-12
Length:	348 ± 2 mm (13.70 inches)
Width:	167 ± 2 mm (6.57 inches)
Container Height:	178 ± 2 mm (7.01 inches)
Total Height (with terminal):	178 ± 2 mm (7.01 inches)
Approx Weight:	Approx 21.0kg (46.3lbs)

Specifications

Terminal Type	Normal Voltage	12V
	Normal Capacity (20HR)	65.0AH
	Standard Terminal	F6
Container Material	Optional Terminal	-
	Standard Option	ABS
Rated Capacity	Flame Retardant Option (FR)	ABS(UL94:VO)
	69.6 AH/3.48A	(20hr, 1.80V/cell, 25°C / 77°F)
	65.0 AH/6.50A	(10hr, 1.80V/cell, 25°C / 77°F)
	56.5 AH/11.3A	(5hr, 1.75V/cell, 25°C / 77°F)
	50.7 AH/16.9A	(3hr, 1.75V/cell, 25°C / 77°F)
Max Discharge Current	40.3 AH/40.3A	(1hr, 1.60V/cell, 25°C / 77°F)
	780A (5s)	
Internal Resistance	Approx 7.3mΩ	
Discharge Characteristics	Operating Temp. Range	Discharge: -15 ~ 50°C (5 ~ 122°F) Charge: 0 ~ 40°C (5 ~ 104°F) Storage: -15 ~ 40°C (5 ~ 104°F)
	Nominal Operating Temp. Range	25 ± 3°C (77 ± 5°F)
	Cycle Use	Initial Charging Current less than 19.50A. Voltage 14.4V ~ 15.0V at 25°C (77°F) Temp. Coefficient -30mV/°C
	Standby Use	No limit on Initial Charging Current Voltage 13.5V ~ 13.8V at 25°C (77°F) Temp. Coefficient -20mV/°C
	Capacity affected by Temperature	40°C (104°F) 103% 25°C (77°F) 100% 0°C (32°F) 86%
	Design Floating Life at 20°C	15 Years
	Self Discharge	Ultracell batteries may be stored for up to 6 months at 25°C(77°F) and then a refresh charge is required. For higher temperatures the time interval will be shorter.

Dimensions

F6 Terminal



ALL DATA IS SUBJECT TO CHANGE WITHOUT NOTICE


Constant Current Discharge (Amperes) at 25°C (77°F)

F.V/Time	10 min	15 min	20 min	30 min	45 min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	76.1	64.0	56.7	47.1	36.3	31.1	20.1	15.1	12.4	10.4	9.13	7.33	6.30	3.36
1.80V/cell	87.0	71.8	62.7	51.1	39.2	32.8	21.6	16.3	13.2	11.1	9.68	7.71	6.50	3.48
1.75V/cell	98.8	80.9	69.3	55.5	42.7	35.8	22.5	16.9	13.6	11.3	10.0	7.97	6.67	3.57
1.70V/cell	111.6	89.8	76.5	60.6	46.0	37.8	23.7	17.8	14.2	12.0	10.5	8.30	6.93	3.66
1.65V/cell	119.9	96.2	81.4	64.0	48.7	39.1	24.6	18.5	14.8	12.3	10.8	8.59	7.13	3.77
1.60V/cell	131.9	105.3	88.4	68.3	50.6	40.3	25.2	19.0	15.1	12.6	11.1	8.73	7.27	3.83


Constant Power Discharge (Watts) at 25°C (77°F)

F.V/Time	10 min	15 min	20 min	30 min	45 min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	142.0	120.6	108.1	90.6	70.5	60.6	39.5	29.8	24.5	20.6	18.1	14.6	12.6	6.72
1.80V/cell	160.6	133.7	117.8	97.0	75.5	63.6	42.1	31.8	25.9	21.8	19.1	15.3	13.0	6.95
1.75V/cell	179.5	148.8	128.9	104.5	81.6	69.0	43.7	33.0	26.7	22.2	19.7	15.8	13.3	7.12
1.70V/cell	198.2	162.8	141.3	113.5	87.5	72.8	45.9	34.6	27.8	23.5	20.6	16.5	13.8	7.29
1.65V/cell	210.9	173.0	149.2	118.8	91.8	74.7	47.3	35.9	28.8	24.1	21.2	17.0	14.2	7.51
1.60V/cell	226.8	186.4	160.3	125.8	94.9	76.6	48.3	36.6	29.4	24.6	21.6	17.2	14.4	7.62


Discharge Characteristics




Float Charging Characteristics




Temperature Effects in Relation to Battery Capacity



Effect of Temperature on Long Term Float Life



Self Discharge Characteristics



- A** No supplementary charge required
(Carry out supplementary charge before use if 100% capacity is required.)
- B** Supplementary charge required before use. Optional charging way as below:
1. Charged for above 3 days at limited current 0.25CA and constant voltage 2.25V/cell.
2. Charged for above 20 hours at limited current 0.25CA and constant voltage 2.45V/cell.
3. Charged for 8~10 hours at limited current 0.05CA.
- C** Supplementary charge may often fail to recover the capacity.
The battery should never be left standing till this is reached.

ALL DATA IS SUBJECT TO CHANGE WITHOUT NOTICE